

Cormix® Pilecon Super Plus

A SUPERIOR PERFORMANCE NATURAL SODIUM BENTONITE

DESCRIPTION

Cormix Pilecon Super Plus is a natural premium grade superior performance sodium bentonite with better filtrate loss, mud cake & gel strength ideally suited for any type of civil engineering applications and on any kind of soil. **Cormix Pilecon Super Plus** performs well in variety of water qualities. **Cormix Pilecon Super Plus** matches API RP-13B Section & OCMA-DFCP4. **Cormix Pilecon Super Plus** swells up to sixteen times its volume and, after dispersion in water, shows rheologic reactions that guarantee highly colloidal suspensions which have high waterproofing and lubricating qualities.

USES & ADVANTAGES

Cormix Pilecon Super Plus is suitable for use with all kinds of soil. It has high filtration properties with low sensitivity to contaminants. It is used in the construction of shafts, micro tunneling, pipe jacking, bore piling, dam grouting diaphragm wall and cavity grouting in segment tunnels.

Advantages include:-

- Reduces fluid loss and prevents water seepage into permeable formations.
- Better filtrate loss, mud cake & gel strength
- Improves bore hole cleaning.
- Transports the excavated material from the face.
- Helps to develop a layer of filter cake on the micro-tunnel front acting as a membrane and inhibiting diffusion of the suspension into ground.
- Reduces jacking force.
- Reduces friction between the pipe & soil.
- Improves the flow of excavated material through the head chamber
- Prevents ground collapsing into the annulus and causing settlement.
- Provides lubrication.
- Little loss of drilling fluids.
- Easy to mix quickly achieves maximum viscosity.

PHYSICAL PROPERTIES

TESTING	RESULT
Moisture:	Max 13%
Specific Gravity:	2.3-2.6
Bulk Density:	850 - 1050 kg/m ³
Swelling - 2 g:	>30 ml
pH at 5 % :	9 - 10.5
Bleeding after 24 hrs:	0
Fineness (pass through 200 mesh)	>75 %
Wet Residue (>200 mesh)	< 3%
Barrel Yield (bbl)	> 120
Residue of Diameter Greater Than 75 µm:	15% Max

TYPICAL CHEMICAL COMPOSITION

SiO ₂	45-55%
Fe ₂ O ₃	4-15%
Al ₂ O ₃	10-19%
TiO ₂	0.8-2.2%
CaO	0.7-2.4%
MgO	1.9-3.6%
Na ₂ O	1.6-3.2%
K ₂ O	0.12-0.30%

APPLICATION

The primary aim of **Cormix Pilecon Super Plus** slurry shall be to ensure that the slurry is capable of fulfilling functions as a retainer, sealant and to stay insular without any deleterious effects on the finished pile, wall or other form of construction. In order to reach the best performance during the preparation of the drilling fluid, **Cormix Pilecon Super Plus** must be dispersed using a turbo mixer in a proportion of 18 - 60 Kg of **Cormix Pilecon Super Plus** per cubic meter of water. **Cormix Pilecon Super Plus** slurry is prepared with an objective to achieve maximum hydration of the bentonite. Therefore **Cormix Pilecon Super Plus** must be added to the mixing water gradually in order to ensure that all the particles are wetted and do not clump into partially hydrated lumps.

Cormix Pilecon Super Plus is suitable for use with khlng water. If there is any doubt about the quality of the water, a chemical treatment should be carried out using sodium bicarbonate or soda ash to control the pH before using **Cormix Pilecon Super Plus**. In addition, for economic and environmental reasons, the maximum re-use and minimum disposal of used slurry is desirable.

Cormix Pilecon Super Plus slurry can be re-used provided its properties are carefully monitored and kept under control. Whatever system of excavation is used, loss of slurry will occur. Some will be excavated with the soil, some will permeate into the strata, and some will become too tainted for re-use and have to be taken off site.

Cormix® Pilecon Super Plus

A SUPERIOR PERFORMANCE NATURAL SODIUM BENTONITE

RHEOLOGICAL PROPERTIES

Cormix Pilecon Super Plus - Mixed with Tap water (334 µs/cm) at 1,500 rpm for 5 min and after 24 hr ageing at 25°C.

TESTING	INSTRUMENT	STANDARD METHOD	STANDARD REQUIREMENT	DOSAGE	MEASUREMENT RESULT
Marsh funnel viscosity	Marsh cone with cup	API RP 13B Section & OCMA DFCP4	30 - 55 Sec	30 kg/M ³ 40 Kg/M ³ 50 Kg/M ³	38 Sec. 46 Sec. 70 Sec.
Fluid density	Mud balance	API RP 13B Section & OCMA DFCP4	Max 1.15 kg/m ³	30 kg/M ³ 40 Kg/M ³ 50 Kg/M ³	1.02 kg/m ³ 1.02 kg/m ³ 1.02 kg/m ³
Fluid loss (@ 30 min, 100 psi)	API-Filter press (LTLP)	API RP 13B Section & OCMA DFCP4	Max 40 ml.	30 kg/M ³ 40 Kg/M ³ 50 Kg/M ³	23 ml 21 ml 18.5 ml
Mud-cake thickness (@ 30 min, 100 psi)		API RP 13B Section & OCMA DFCP4	< 3 mm.	30 kg/M ³ 40 Kg/M ³ 50 Kg/M ³	1.62 mm 1.97 mm 2.92 mm
pH	pH indicator strips (Litmus paper)	API RP 13B Section & OCMA DFCP4	9.5 - 11.7	30 kg/M ³ 40 Kg/M ³ 50 Kg/M ³	8 - 9 8 - 9 8 - 9

PACKAGING

25 kg bags. or 1.30 MT bags.

STORAGE & SHELF LIFE

Cormix Pilecon Super Plus has a shelf life of 12 months when stored in a dry place below 35°C in unopened condition.

HEALTH & SAFETY

Cormix Pilecon Super Plus is alkaline, use protective gloves, glasses and protect skin. If gets into eyes clean out with water immediately, wash off skin with soap and water immediately.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001: 2015 verified by TUV Nord.

ISO 14001: 2015 verified by Lloyd's Register International.

DISCLAIMER

Performance data is achieved testing in accordance with International Standards. Testing by others may result in different results from those published as a result of external factors such as poor sampling, incorrect mixing, varying temperatures, curing, crushing procedures etc.

Cormix does not take responsibility nor need to defend others testing that does not achieve the published data.

The user must test the products suitability for the intended application and purpose. Cormix reserves the right to change the properties of the product.

Site conditions and differences in materials are such that no warranty or fitness for a particular purpose, nor liability can be inferred from the published data sheet, written recommendations or from other advise offered.

CONTACT DETAILS

Cormix International Limited

89 Romklao Rd., Sansab, Minburi, Bangkok 10510

Tel. (66 2) 917 3955-8

Website: <http://www.cormix.com>

Email Address: info@cormix.com

NOTE : Every reasonable precaution is taken in the manufacture of all CORMIX-products to ensure that they comply with CORMIX's high standard of quality. The recommendations and properties of the product are based upon what is believed to be the most reliable information available and are not intended as recommendations which infringe on other patents. Although all CORMIX-products are subject to rigid quality tests, no specific guarantee can be given, because results depend, not only on quality, but also on other factors beyond our control. We welcome therefore consultation in the event of doubt concerning application, or performance, and point out those oral recommendations, which vary from the instructions contained herein, are not binding without written confirmation by CORMIX. All transactions shall be subject to our terms and conditions of sale-delivery-and-service. This data sheet supersedes the previous one and a reprint may be issued without notice to supersede this edition, as and when deemed necessary. The information given in this leaflet is to the best of our knowledge true and reliable. Field service where provided does not constitute supervisory responsibility. Our guarantee is therefore limited to the quality of materials delivered.