

Cormix® LA1

LIQUID ACCELERATOR FOR BACKFILL GROUT

DESCRIPTION

Cormix LA1 is a liquid accelerator used for cementitious grouting in tunnels driven by TBMs.

USES & ADVANTAGES

Cormix LA1 is suitable for use in tunnel grouting applications where an early strength is required for the backfill grout after a few hours. It is used with Tunnel Boring Machines and used for primary tail shield grouting or secondary grouting through segmental lining. The main advantages of **Cormix LA1** is that the grouts gelling time is speeded up and early strengths are achieved within 1-2 hours.

PROPERTIES

Appearance:	Clear liquid
Specific Gravity:	Approx. 1.30-1.43 at 25°C
Air Entrainment:	Nil
Chloride Content:	Nil

Compatibility with Cements:

Cormix LA1 can be used with all types of Portland Cements

Compatibility with Other Admixtures:

Cormix LA1 should not be premixed with other admixtures. The performance of the material may be affected by the presence of other chemicals. **Cormix International Limited** should be consulted in such circumstances.

MIXING

Cormix LA1 should be introduced into the grout mix at or near the nozzle of the grout line.

DOSAGE

The performance of **Cormix LA1** is best assessed by preliminary trials on site. The dosage can be varied to achieve the required gel time, early & final strength. The gel time is dependent upon the grout mix & dosage of **Cormix LA1**.

Note: The reaction involved is temperature dependent and will proceed more slowly in cold ambient conditions. Fresh cement reacts more quickly than old cement.

PACKAGING

Cormix LA1 is supplied in 200 litre drums.

STORAGE & SHELF LIFE

Cormix LA1 should preferably be stored inside, away from moisture contact and protected from frost. In original unopened drums shelf life is 12 months.

HEALTH & SAFETY

Caution: Cormix LA1 is caustic. Avoid contact with the skin, eyes and clothing. In all cases of contact, wash thoroughly with water. Immediate medical attention must be sought for all cases of ingestion or eye contact. Gloves, mask, goggles and protective clothing should be worn when handling or using **Cormix LA1**.

TECHNICAL SERVICE

The Cormix International Technical Service Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

QUALITY ASSURANCE

ISO 9001 : 2015 verified by TUV Nord.
ISO 14001 : 2015 verified by Lloyd's Register International.

DISCLAIMER

Performance data is achieved testing in accordance with International Standards. Testing by others may result in different results from those published as a result of external factors such as poor sampling, incorrect mixing, varying temperatures, curing, crushing procedures etc.

Cormix does not take responsibility nor need to defend others testing that does not achieve the published data. The user must test the products suitability for the intended application and purpose. **Cormix** reserves the right to change the properties of the product. Site conditions and differences in materials are such that no warranty or fitness for a particular purpose, nor liability can be inferred from the published data sheet, written recommendations or from other advise offered.

CONTACT DETAILS

Cormix International Limited

89 Romkiao Rd., Sansab, Minburi, Bangkok 10510
Tel. (66 2) 917 3955-8
<http://www.cormix.com>
E-mail: info@cormix.com

Rev.008 Nov 2023